



PCT/GB2004/005145




INVESTOR IN PEOPLE

The Patent Office  
Concept House  
Cardiff Road  
Newport  
South Wales  
NP10 8QQ

## PRIORITY DOCUMENT

SUBMITTED OR TRANSMITTED IN  
COMPLIANCE WITH RULE 17.1(a) OR (b)




I, the undersigned, being an officer duly authorised in accordance with ~~Section 74(1) and (4)~~ of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.




Signed

*William Morell*

Dated

23 December 2004

## Patents Form 1/77

Patents Act 1997  
(Rule 16)11DEC03 E858712-1 D02877  
P01/7700 0.00-0328693.7 ACCOUNT CHA

1/77

## Request for grant of a patent

(see the notes on the back of this form. You can also get  
an explanatory leaflet from the Patent office to help  
you fill in this form)

The Patent Office

Cardiff Road  
Newport  
Gwent NP9 1RH

1 Your reference

UOI 51122

2 Patent application number  
(The Patent Office will fill in this part)

0328693.7

3 Full name, address and postcode of the or of  
each applicant (underline all surnames)Imperial Chemical Industries PLC, 20 Manchester Square,  
London, W1U 3AN

&amp;

ICI Americas Inc. Law Department  
10 Findeme Avenue  
NJ 08807  
USA

Patents ADP Number (if you know it)

If the applicant is a corporate body, give the  
country/state of its incorporation

United Kingdom

4 Title of the invention

Metal Oxide Dispersions

5 Name of Your Agent (if you have one)

HUMPHRIES, Martyn

"Address for service" in the United Kingdom  
to which all correspondence should be sent  
(including the postcode)Uniqema Intellectual Property Dept  
Wilton Centre  
Wilton  
Redcar  
England, TS10 4RF

Patents ADP Number (if you know it)

6 If you are declaring priority from one or more  
earlier patent applications, give the country  
and the date of filing of the or each of theseCountry Priority Application number Date of Filing  
(if you know it) (day / month / year)7 If this application is divided or otherwise derived from an  
earlier UK application, give the number and filing date of  
the earlier applicationNumber of earlier application Date of Filing  
(day / month / year)8 Is a statement of inventorship and of right to grant of a  
patent required in support of this request?

Yes

Answer yes if:

- a) any applicant named in part 3 is not an inventor, or
  - b) there is an inventor who is not named as an applicant, or
  - c) any named applicant is a corporate body.
- See Note (d)

## Patents Form 1/77

## Patents Form 1/77

- 9 Enter the number of sheets for any of the following items you are filing with this form. Do not count copies of the same document

Continuation sheets of this form -

Description 9

Claim(s) 1

Abstract 1

Drawings

- 10 If you are also filing any of the following state how many against each item

Priority documents

Translations of priority documents

Statement of Invention and right to grant of a patent (Patents Form 7/77)

Request for Preliminary Examination and search (Patents Form 9/77)

Request for Substantive Examination (Patents Form 10/77)

Any other documents (Please specify)

- 11 I/We request the grant of a patent on the basis of this application

Signature *M. M. W.*

Date 11.12.03

- 12 Name and daytime telephone number of person to contact in the United Kingdom

HUMPHRIES, Martyn

01642 435337

## Warning

*After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been issued, or any such direction has been revoked.*

## Notes

- a) If you need help to fill in this form or you have any questions, please contact the Patent Office on 0645 500505
- b) Write your answers in capital letters using black ink or you may type them.
- c) If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.
- d) If you answered 'Yes' Patents Form 7/77 will need to be filed.
- e) Once you have filled in the form you must remember to sign and date it.
- f) For details of the fee and ways to pay please contact the Patent Office.

UQI 51122

1

**METAL OXIDE DISPERSIONS****Field of Invention**

5 This invention relates to dispersions of metal oxides and in particular to dispersions of metal oxides in a siloxane fluid dispersing medium having a polysiloxane containing a carboxyl group as dispersing agent.

**Background**

10 Metal oxides such as titanium dioxide, zinc oxide and iron oxides have been employed as attenuators of ultraviolet light in applications such as sunscreens, plastics films and resins. Generally, metal oxides which are useful in these applications have an average primary particle size less of than 200 nm. Dispersions of such metal oxides in certain oily media and in water are known and these dispersions have been used to formulate products such as suncreening creams and lotions. The availability of the metal oxide in the form of a dispersion which is subsequently mixed with other  
15 conventional formulation ingredients to prepare a product has been shown to be advantageous in preparing the products.

The use of siloxane or silicone based oils in cosmetics has become popular because they can produce an improved skin feel. Hence, metal oxide dispersions in siloxane based dispersing media are desirable. Such dispersions have been difficult  
20 to produce.

**Prior Art**

EP-0953336-A discloses a method for producing a dispersion of ultraviolet shielding fine particles in a silicone oil using a modified silicone or reactive silicone dispersant and a mill or high pressure dispersion treatment. EP-0953336-A is  
25 particularly directed to the use of oxazoline-modified silicones, amino-modified silicones and polyether-modified silicones. EP-0953336-A discloses a maximum concentration of 40% by weight of particles, although the examples in the patent specification contain significantly lower amounts of particles. There is a need for a siloxane or silicone based dispersion containing a higher concentration of particles, in  
30 order to improve the flexibility to the sunscreen formulator. There is also a requirement for such a dispersion to have improved properties, such as stability and optical characteristics.

**Summary of the Invention**

35 We have now surprisingly discovered a dispersion, which overcomes or significantly reduces at least one of the aforementioned problems.

Accordingly the present invention provides a dispersion comprising particles of metal oxide dispersed in a siloxane fluid and a dispersing agent which is a polysiloxane comprising in the range from 0.1 to 3 carboxyl groups per molecule.

UQI 51122

2

The invention further provides a method of preparing a dispersion of metal oxide which comprises milling with a particulate grinding medium particles of metal oxide in a siloxane fluid in the presence of a dispersing agent which is a polysiloxane comprising in the range from 0.1 to 3 carboxyl groups per molecule.

By dispersion is meant a true dispersion, i.e. where the solid particles are stable to aggregation. The particles in the dispersion are relatively uniformly dispersed and resistant to settling out on standing, but if some settling out does occur, the particles can be easily redispersed by simple agitation.

The polysiloxane dispersing agent is preferably a polyalkylsiloxane, wherein the alkyl groups are preferably lower alkyl, such as C<sub>1-6</sub>, more preferably C<sub>1-3</sub>, and particularly methyl groups.

By carboxyl group of the polysiloxane is meant a free functional carboxyl group and/or ester and/or salt derivative thereof. Suitable ester groups include lower alkyl, such as C<sub>1-6</sub>, preferably C<sub>1-3</sub>, and particularly methyl groups. Suitable salt derivatives include metal, such as alkali metal, preferably sodium or potassium. In a preferred embodiment of the invention, the carboxyl group of the polysiloxane is in the form of the free acid and/or salt thereof, and more preferably in the form of the free acid.

The polysiloxane suitably comprises in the range from 0.5 to 3, preferably 0.8 to 2.5, more preferably 0.9 to 2, particularly 1 to 1.5, and especially 1.1 to 1.4 carboxyl groups (or carboxyl group containing monomer units) per molecule; in a preferred embodiment, a mixture of polysiloxane molecules containing different numbers of carboxyl groups are employed, and therefore the number of carboxyl groups per molecule is an average value (by number) and may be a non-integer.

In addition, the polysiloxane suitably comprises in the range from 20 to 500, preferably 30 to 200, more preferably 40 to 150, particularly 50 to 120, and especially 60 to 100 non-carboxyl group containing monomer units per molecule.

The ratio of non-carboxyl group containing monomer units to carboxyl group containing monomer units in the polysiloxane is suitably in the range from 30 to 150:1, preferably 40 to 100:1, more preferably 45 to 75:1, particularly 50 to 70:1, and especially 55 to 65:1.

The carboxyl group(s) is preferably attached terminally and/or laterally, more preferably laterally, and particularly only laterally, to the polysiloxane chain suitably through a hydrocarbon linkage which may contain a hetero atom. In a preferred embodiment of the invention, the carboxyl group is attached through a hydrocarbon linkage which comprises a pyrrolidone group.


The polysiloxane suitably has a molecular weight (number average), preferably measured by gel permeation chromatography, in the range from 500 to 50,000, preferably 2,000 to 20,000, more preferably 4,000 to 15,000, particularly 5,000 to 10,000, and especially 6,000 to 8,000.

UQI 51122

3


The polysiloxane suitably has a viscosity in the range from 0.05 to 150, preferably 0.1 to 50, more preferably 0.2 to 10, particularly 0.5 to 5, and especially 0.7 to 1.2 Pa.s.

The polysiloxane preferably has the formula (1) below:



5

wherein:  $\text{R}_1$ , which can be the same or different, is selected from  $\text{R}_2$ , H, a primary amine containing group, and a pyrrolidone containing a carboxyl group and/or ester and/or salt derivative thereof of the formula (2):



10

wherein 0.1 to 3 of the  $\text{R}_1$  groups is of the formula (2);

$\text{F}$ , can be the same or different, is linear or branched alkylene of 1-12 carbon atoms;

$n$  is zero or 2;  $n^1$  is zero or 1;  $n^2$  is zero or 1; with the proviso that when  $n$  is 0 and  $n^2$  is 1,  $n^1$  is 1, when  $n$  is 2 and  $n^2$  is 1,  $n^1$  is 0 or 1 and when  $n$  is 2 and  $n^2$  is 0,  $n^1$  is 0;

15

$\text{B}$  is  $-\text{NR}_9$ , sulphur (S) or oxygen (O), wherein  $\text{R}_9$  is hydrogen or lower alkyl ( $\text{C}_{1-6}$ );

$\text{R}_2$  can be the same or different and is selected from alkyl, aryl and olefinic (vinyl);

$\text{R}_3$  and  $\text{R}_4$ , can be the same or different, are selected from alkyl, aryl, capped or uncapped polyoxyalkylene, alkaryl, aralkylene and alkenyl;

20

$\text{R}_5$  is hydrogen, lower alkyl ( $\text{C}_{1-6}$ ) or a metal;

$a$  can be an integer in the range from 10 to 1,000; and

$b$  can be an integer in the range from 0 to 3.

UQI 51122


4

In a preferred embodiment of the invention,  $R_5$  is hydrogen or alkali metal, more preferably hydrogen.  $R_1$  is preferably  $R_2$  or a pyrrolidone containing a carboxyl group and/or ester and/or salt derivative thereof. At least one laterally linked  $R_1$  group is preferably a pyrrolidone containing a carboxyl group and/or ester and/or salt derivative thereof.  $R_3$  and  $R_4$  are preferably alkyl, more preferably lower alkyl  $C_{1-6}$ , particularly  $C_{1-3}$ , and especially methyl.

Suitably  $a$ , which may be an integer, is in the range from 20 to 500, preferably 30 to 200, more preferably 40 to 150, particularly 50 to 120, and especially 60 to 100. In addition  $b$ , which may be an integer, may be in the range from 0.1 to 3, suitably 0.5 to 3, preferably 0.8 to 2.5, more preferably 0.9 to 2, particularly 1 to 1.5, and especially 1.1 to 1.4. The ratio of  $a:b$  is suitably in the range from 30 to 150:1, preferably 40 to 100:1, more preferably 45 to 75:1, particularly 50 to 70:1, and especially 55 to 65:1.

Both terminal  $R_1$  groups are preferably  $R_2$ .  $R_2$  is preferably alkyl, more preferably lower alkyl  $C_{1-6}$ , particularly  $C_{1-3}$ , and especially methyl.  $B$  is preferably  $-NR_6$ . In a particularly preferred embodiment of the invention,  $n$  is 2,  $n^1$  is 0,  $n^2$  is 0 and  $F$  is  $CH_2$  or  $n$  is 2,  $n^1$  is 0,  $n^2$  is 1,  $B$  is  $NCH_3$  and  $F$  is  $CH_2$ , and especially  $n$  is 2,  $n^1$  is 0,  $n^2$  is 0 and  $F$  is  $CH_2$ .

In a particularly preferred embodiment of the invention, the polysiloxane dispersing agent preferably has the formula (3) below:



wherein  $X$  is hydrogen or alkali metal,  $a$ ,  $b$ , and the ratio of  $a:b$  are as defined above.

US-5596061-A, the teaching of which is incorporated herein by reference, discloses suitable polysiloxanes containing a carboxyl group, and methods of synthesis thereof, for example by reacting a polysiloxane having a functional primary amine group with itaconic acid.

UQI 51122

5

The amount of polysiloxane dispersing agent present in the dispersion according to the present invention is preferably in the range from 1 to 60%, more preferably 3 to 40%, particularly 5 to 30%, and especially 6 to 25% by weight based on the weight of particles of metal oxide.

5 Preferably the metal oxide used in the invention comprises an oxide of titanium, zinc or iron, more preferably is titanium dioxide or zinc oxide, and particularly zinc oxide.

10 The average primary particle size of the particles of metal oxide is preferably less than 200 nm, and where the particles are substantially spherical then this size will be taken to represent the diameter. However, the invention also encompasses particles of metal oxides which are non-spherical and in such cases the average primary particle size refers to the largest dimension. The average particle size which characterises the metal oxides used in the invention is the average size of primary particles, this average size typically being determined by electron microscopy. The  
15 size therefore relates to particles of metal oxide which are not aggregated. Frequently, the primary particles consist of single crystals but may also comprise several crystals fused together.

20 Preferably the average primary particle size of the particles is in the range from 5 to 150 nm, and more preferably 10 to 100 nm when they are substantially spherical. For titanium dioxide particles having an acicular shape the average largest dimension of the primary particles is preferably less than 150 nm, and more preferably in the range from 20 to 100 nm.

25 When the metal oxide is titanium dioxide the particles are preferably acicular in shape and have a ratio of largest dimension to shortest dimension in the range from 10:1 to 2:1. Also, when the metal oxide is titanium dioxide the amount of polysiloxane dispersing agent present in the dispersion is preferably in the range 5 to 60%, more preferably 9 to 40%, particularly 12 to 30%, and especially 15 to 25% by weight based on the weight of particles of titanium dioxide.

30 When the metal oxide is zinc oxide the particles suitably have an average primary particle size in the range from 30 to 100 nm, and preferably 60 to 90 nm. Also, when the metal oxide is zinc oxide the amount of polysiloxane dispersing agent present in the dispersion is preferably in the range 1 to 25%, more preferably 3 to 18%, particularly 5 to 12%, and especially 6 to 9% by weight based on the weight of particles of zinc oxide.

35 The particles of metal oxide may comprise substantially pure metal oxide but preferably also carry an inorganic coating. For example, particles of titanium dioxide can be coated with oxides of other elements such as oxides of aluminium, zirconium or silicon and a form of acicular titanium dioxide, coated with alumina and silica, which is especially useful in the process of this invention is disclosed in GB-2205088-A.



UQI 51122

6

Alternatively, particulate metal oxides which carry alumina as the only inorganic oxide coating have also been found to be useful in this invention. The preferred amount of inorganic coating is in the range 4 to 20 per cent by weight, calculated as inorganic oxide with respect to weight of metal oxide core particles. More preferably, the amount of inorganic coating is in the range from 5 to 15% by weight, calculated as inorganic oxide with respect to weight of metal oxide core particles. Suitable inorganic coatings can be applied using any appropriate technique and a person skilled in the art will readily be able to apply such a technique. A typical process comprises forming an aqueous dispersion of metal oxide core particles in the presence of a soluble salt of the inorganic element whose oxide will form the coating. This dispersion is usually acidic or basic, depending upon the nature of the salt chosen, and precipitation of the inorganic oxide is achieved by adjusting the pH of the dispersion by the addition of acid or alkali, as appropriate.

In a preferred embodiment, the metal oxide particles used to form dispersions of the invention are hydrophobic. The metal oxide particles may be rendered hydrophobic, for example, by application of a hydrophobic coating on the surface of the metal oxide particles. The hydrophobic coating may be applied prior to formation of the dispersion, or alternatively in situ, ie during dispersion formation. In addition, as described above, the particles may carry an inorganic coating. Therefore, the term "particles of metal oxide", as used herein is taken to mean the complete particles, i.e. the core particles plus any coating which has been applied.

Generally, the metal oxide particles are treated with a water-repellent material in order to render them hydrophobic. Suitable water-repellent materials include fatty acids, preferably fatty acids containing 10 to 20 carbon atoms, such as lauric acid, stearic acid and isostearic acid, salts of the above fatty acids such as sodium salts and aluminium salts, fatty alcohols, such as stearyl alcohol, and silicones such as polydimethylsiloxane and substituted polydimethylsiloxanes and reactive silicones such as methylhydrosiloxane polymers and copolymers.

The hydrophobic treatment can be applied using any conventional process. Typically, metal oxide core particles (uncoated or with an inorganic coating) are dispersed in water and heated to a temperature in the range 50 to 80°C. A fatty acid is then deposited on the metal oxide particles by adding a salt of the fatty acid (e.g. sodium stearate) to the dispersion, followed by an acid. Alternatively, the metal oxide core particles or inorganically coated core particles can be mixed with a solution of the water-repellent material in an organic solvent, followed by evaporation of the solvent. In an alternative embodiment of the invention, the water-repellant material can be added directly to the dispersion of the present invention, during preparation thereof, such that the hydrophobic coating is formed in situ.

UOI 51122

7

Generally, the particles are treated with up to 20% by weight of the water-repellent material, calculated with respect to the coated or uncoated core particles, as appropriate, and preferably in the range from 0.05 to 3% by weight of water-repellent material, calculated with respect to coated or uncoated core particles.

5 The dispersion according to the present invention suitably contains greater than 30%, preferably greater than 40%, more preferably greater than 45%, particularly greater than 50%, and especially greater than 60% by weight of particles of metal oxide, particularly zinc oxide, based on the total weight of the dispersion. Generally it is difficult to produce dispersions containing greater than 75% by weight of particles of  
10 metal oxide.

The metal oxide used in the dispersion of the invention is dispersed in a siloxane fluid dispersing medium. Any suitable siloxane fluid can be used, a principal requirement being cosmetic acceptability. One preferred type of siloxane fluid is a cyclic oligomeric dialkylsiloxane, such as the cyclic pentamer of dimethylsiloxane  
15 known as cyclomethicone. Alternative fluids include dimethylsiloxane linear oligomers or polymers having a suitable fluidity and phenyltris(trimethylsiloxy)silane (also known as phenyltrimethicone).

The dispersion may further contain conventional additives suitable for use in the intended application for the dispersion, such as conventional cosmetic ingredients  
20 used in sunscreens. Preferably, for maximum flexibility of use, the dispersion consists essentially of the specified ingredients (particles of metal oxide, siloxane fluid dispersing medium and carboxyl group containing polysiloxane dispersing agent).

The dispersions of the invention are particularly useful for preparing sunscreen products and other compositions intended to attenuate ultraviolet light. For such  
25 applications it is desirable that the dispersion strongly attenuates ultraviolet light but in use, i.e. when applied to the skin in a sunscreen formulation, is substantially transparent to visible light. When the metal oxide is titanium dioxide the dispersions preferably have a maximum extinction coefficient for light in the ultraviolet range of wavelengths of at least 40, more preferably at least 50 litres per gram per cm.  
30 When the metal oxide is zinc oxide the dispersions preferably have a maximum extinction coefficient for light in the ultraviolet range of wavelengths of at least 15, more preferably at least 20 litres per gram per cm.

The particles of metal oxide in a dispersion which in use is substantially transparent to visible light will have an extinction coefficient for light in the visible range of  
35 wavelengths preferably not greater than 10, more preferably not greater than 5 litres per gram per cm.

The dispersions of metal oxides according to the present invention are preferably prepared by milling with a particulate grinding medium. A suitable mill which is employed to effect the grinding of the metal oxide product in the dispersing medium is

UOI 51122

8

one which uses a particulate grinding medium to grind the product. Typical of such mills are bead mills equipped with one or more agitators and using sand, glass beads or ceramic beads or other particles as the particulate grinding medium. Particularly useful are those mills which operate at a high speed and, depending on the size of mill, a speed in the range 500 to 5000 rev. per minute (r.p.m) is generally suitable. Preferably, mills operating at a speed in the range 800 r.p.m to 3000 r.p.m are used. Agitator mills in which the tip speed of the agitator is up to and can exceed 10 metres per second are of use. If desired the mill can be cooled. Generally, the dispersions are pre-mixed before milling using a high speed stirrer, but, in an alternative process, the dispersing medium is added to the mill initially and then the metal oxide and the dispersing agent co-added to the dispersing medium subsequently. After milling has been carried out for the required time the dispersion is separated from the grinding medium by screening through a narrow gap.

Generally, this method can be used to prepare dispersions possessing the properties of the dispersions of the invention mentioned hereinbefore. In particular, dispersions which strongly attenuate ultraviolet light but in use are substantially transparent to visible light can be prepared using the method. Frequently, it is possible to adjust the light attenuating profile by adjusting the conditions (e.g. length of time, proportion of grinding medium, concentration of dispersing agent or metal oxide) under which the milling is carried out.

The dispersions of the invention are useful as ingredients for preparing end-use sunscreen compositions. The amount of metal oxide present in the sunscreen composition is preferably in the range from 0.5 to 30%, and more preferably 2.0 to 20% by weight of the composition. The metal oxide particles may provide the only ultraviolet light attenuators in the sunscreen composition, but other sunscreens agents, particularly organic sunscreens, may also be added.

The invention is illustrated by the following non-limiting example.

The following test procedures were employed:

- i)  $^{29}\text{Si}$  NMR was used to measure the number of non-carboxyl group containing monomer units (or a in formulae (1) and (3)), the number of carboxyl group containing monomer units (or b in formulae (1) and (3)), the a:b ratio, and the molecular weight of the polysiloxane dispersing agent.
- ii) Viscosity was measured using a Brookfield RVT viscometer at 25°, and results are quoted in Pa.s.

#### Example

86.25 g of cyclomethicone, 11.25 g of Monasil PCA (ex Uniqema) and 150 g of hydrophobically coated zinc oxide having an average primary particle size of approximately 80 nm (calculated from specific surface area) were mixed together and thoroughly agitated for 15 minutes. The mixture was then passed through a horizontal

UQI 51122

9

bead mill operating at approximately 1500 r.p.m. and containing zirconia beads as grinding media. The mixture was passed through the mill and was then returned to the pre-mix vessel and passed through the mill a further three times. The optical characteristics of the resulting dispersion (as determined by UV spectrometry after dilution by a factor of 20,000 using n-octanol) are given in Table 1 below, where  $\lambda_{\max}$  is the wavelength in nm at which maximum attenuation was observed and  $E_{\max}$ ,  $E_{308}$ ,  $E_{360}$  and  $E_{524}$  are the observed extinction coefficients in l/g/cm at  $\lambda_{\max}$ , 308 nm, 360 nm and 524 nm respectively.

10

Table 1

$\lambda_{\max}$	$E_{\max}$	$E_{308}$	$E_{360}$	$E_{524}$
374	17.0	13.3	14.2	2.8

UQI 51122

10

CLAIMS

1. A dispersion comprising particles of metal oxide dispersed in a siloxane fluid and a dispersing agent which is a polysiloxane comprising in the range from 0.1 to 3 carboxyl groups per molecule.
- 5 2. A dispersion according to claim 1 wherein the polysiloxane has a viscosity in the range from 0.2 to 10 Pa.s.
3. A dispersion according to either one of claims 1 and 2 wherein the polysiloxane has a molecular weight (number average) in the range from 4,000 to 15,000.
4. A dispersion according to any one of the preceding claims wherein the dispersion  
10 comprises greater than 30%, more preferably greater than 40%, and particularly greater than 50% by weight of particles of metal oxide.
5. A dispersion according to any one of the preceding claims wherein the polysiloxane comprises 0.8 to 2.5 carboxyl groups per molecule.
6. A dispersion according to any one of the preceding claims wherein the  
15 polysiloxane comprises in the range from 30 to 200 non-carboxyl group containing monomer units.
7. A dispersion according to any one of the preceding claims wherein the carboxyl group is attached laterally, preferably only laterally, to the polysiloxane chain.
8. A dispersion according to any one of the preceding claims wherein the metal  
20 oxide particles are hydrophobic.
9. A dispersion according to any one of the preceding claims wherein the siloxane fluid dispersing medium is a cyclic oligomeric dialkylsiloxane, a linear dimethyl-siloxane oligomer and/or polymer, and/or phenyltris(trimethylsiloxy)silane.
10. A method of preparing a dispersion of metal oxide which comprises milling with a  
25 particulate grinding medium particles of metal oxide in a siloxane fluid in the presence of a dispersing agent which is a polysiloxane comprising in the range from 0.1 to 3 carboxyl groups per molecule.

UQI 51122

11

**Abstract**

A dispersion contains particles of metal oxide dispersed in a siloxane fluid and a dispersing agent which is a polysiloxane containing in the range from 0.1 to 3 carboxyl groups per molecule. The dispersion is particularly suitable for use as an ingredient in sunscreening cosmetics.

5